

Appl No. 10/594,784  
Response Dated February 9, 2009  
Reply to Office Action of October 10, 2008

**Amendments to the Claims:**

This listing will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

Claim 1 (Previously presented): An acrylic elastomer composition, which comprises a carboxyl group-containing acrylic elastomer, (A) a vulcanizing agent of polyvalent amine compound, and (B) an antioxidant comprising a thiazole-based compound selected from 2-mercaptobenzothiazole, or its zinc salt, or dibenzothiazyl disulfide, wherein the thiazole-based compound inhibits oxidative degradation of compression set characteristics of said acrylic elastomer composition.

Claim 2 (Original): An acrylic elastomer composition according to Claim 1, wherein the carboxyl group-containing acrylic elastomer is an aliphatic unsaturated dicarboxylic acid monoalkyl ester-copolymerized acrylic elastomer.

Claim 3 (Original): An acrylic elastomer composition according to Claim 1, wherein 0.05-10 parts by weight of the thiazole-based compound is contained on the basis of 100 parts by weight of the carboxyl group-containing acrylic elastomer.

Appl. No. 10/594,784  
Response Dated February 9, 2009  
Reply to Office Action of October 10, 2008

Claim 4 (Original): An acrylic elastomer composition according to Claim 2, wherein 0.05-10 parts by weight of the thiazole-based compound is contained on the basis of 100 parts by weight of the carboxyl group-containing acrylic elastomer.

Claim 5 (Original): An acrylic elastomer composition according to Claim 1, wherein the thiazole-based compound is used together with an amine-based or phenol-based antioxidant.

Claim 6 (Original): An acrylic elastomer composition according to Claim 2, wherein the thiazole-based compound is used together with an amine-based or phenol-based antioxidant.

Claim 7 (Previously presented): An acrylic elastomer composition according to Claim 1, wherein 0.1-5 parts by weight of a vulcanizing agent of polyvalent amine compound is further contained on the basis of 100 parts by weight of the carboxyl group-containing acrylic elastomer.

Claim 8 (Original): An acrylic elastomer vulcanization-molded article, vulcanization-molded from an acrylic elastomer composition according to Claim 1.

Claim 9 (Canceled)

Appl. No. 10/594,784  
Response Dated February 9, 2009  
Reply to Office Action of October 10, 2008

**Claim 10 (Original):** An acrylic elastomer vulcanization-molded article according to Claim 8, which has parts in a wall thickness of not more than 30mm.

**Claim 11 (Canceled)**

**Claim 12 (Original):** An acrylic elastomer vulcanization-molded article according to Claim 10, wherein the vulcanization-molded article having parts in a wall thickness of not more than 30mm is a gasket or O ring.

**Claim 13 (Canceled)**

**Claim 14 (New):** A method of improving the compression set characteristics of an acrylic elastomer composition which comprises a carboxyl group-containing acrylic elastomer, which method comprises using a vulcanizing agent of a polyvalent amine compound to prepare the acrylic elastomer composition and incorporating a thiazole-based compound selected from 2-mercaptobenzothiazole, or its zinc salt, or dibenzothiazyl disulfide into the acrylic elastomer composition.

**Claim 15 (New):** A method of improving the compression set characteristics of an acrylic elastomer composition according to claim 14, wherein the thiazole-based compound inhibits oxidative degradation of compression set characteristics of said acrylic elastomer composition.

Appl. No. 10/594,784  
Response Dated February 9, 2009  
Reply to Office Action of October 10, 2008

Claim 16 (New) A method of improving the compression set characteristics of an acrylic elastomer composition according to claim 14 further comprising including an amine-based or phenol-based antioxidant into the acrylic elastomer composition, which functions as a primary antioxidant.